



Cold crack resistance to -58°F
Exceptional strength & durability

	■ Technical properties	Standards
Yarn	1100 dtex PES HT	TERSUISSE 6
Finish	Varnish both sides	
Weight	19.7 oz/yd ²	EN ISO 2286-2
Width	106.3 in	
Standard length	54.6 yds / 382.7 yds	
Tensile strength (warp/weft)	250/250 daN/5 cm	EN ISO 1421
Tear strength (warp/weft)	35/35 daN	DIN 53.363
Adhesion	10/10 daN/5 cm	EN ISO 2411
Flexibility (warp/weft)	6.5/8.5	ASTM D5342
Scrub	>2,000 cycles	EN ISO 5981
Cold crack resistance	-58°F, no cracking or flaking at folds	ASTM D751, 61-65
Flame retardancy	40 mm/min	ISO 3795

■ Certifications, labels, warranties

**Precontraint[®]
technology**

■ Colors & references

- consult us for availability
- special production runs available on request

The technical data above are average values with a +/- 5% tolerance. The buyer of our products is fully responsible for their application or their transformation concerning any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, use and customs and safety rules of the countries where they are used. For information on our contractual warranty, please refer to the relevant terms and conditions. The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subjects to evolutions due to technical progress, we remain entitled to modify the characteristics of our products at any time. The buyer of our products is responsible for checking the validity of the above data.