



NEUMANN

ZELTE & PLANEN

J. Neumann GmbH
Heinrich-Hasemeier-Straße 35
49076 Osnabrück

Tel.: 0541-45167
Fax: 0541-430967
www.neumann-zelte.de
www.neumann-planen.de

PVC - Planenstoff 680

					
867 (Ral 9010) 2,50, 3,00m 30-60-250 ml	7455 (Ral 9016) 2,50m 30-60-250 ml	7457 (Ral 1013) 2,50m 30-60-250 ml	7458 (Ral 1015) 2,50m 30-60-250 ml	7443 (Ral 1014) 2,50m 30-60-250 ml	7440 (Ral 1018) 2,50m 30-60-250 ml
					
7441 (Ral 1021) 2,50, 3,00m 30-60-250 ml	7456 (Ral 1003) 2,50, 3,00 m 30-60-250 ml	7445 (Ral 2008) 2,50m 30-60-250 ml	7444 (Ral 2004) 2,50m 30-60-250 ml	7447 (Ral 3020) 2,50m 30-60-250 ml	7446 (Ral 3002) 2,50, 3,00m 30-60-250 ml
					
887 (Ral 8017) 2,50m 30-60-250 ml	7449 (Ral 5012) 2,50m 30-60-250 ml	7450 (Ral 5015) 2,50m 30-60-250 ml	7307 (Ral 5010) 2,50m 30-60-250 ml	941 1,50, 2,50, 3,00m 30-60-250 ml	7290 (Ral 5002) 2,50m 30-60-250 ml
					
7448 (Ral 5003) 2,50m 30-60-250 ml	7309 (Ral 5013) 2,50m 30-60-250 ml	7451 (Ral 6005) 2,50m 30-60-250 ml	7454 (Ral 6028) 2,50m 30-60-250 ml	995 (Ral 6026) 2,50, 3,00m 30-60-250 ml	7452 (Ral 6018) 3,00m 30-60-250 ml
					
7459 (Ral 7035) 2,50m 30-60-250 ml	7374 (Ral 7038) 2,50m 30-60-250 ml	7344 2,50m 30-60-250 ml	939 2,50, 3,00m 30-60-250 ml	7300 (Ral 9006) 2,50, 3,00m 30-60-250 ml	7196 (Ral 7037) 2,50m 30-60-250 ml
					
810 (Ral 9005) 2,50m 30-60-250 ml					

Technische Daten:

Material:	Sehr strapazierfähiges Polyester 1100 dtex
Gewicht:	680 g/m ²
Weiterreißfestigkeit:	32/28 daN
Reißfestigkeit:	260/250 daN
Haftfestigkeit:	10 daN/5cm
Brennverhalten:	DIN 75200 (<100mm/mm)
Temperaturbeständigkeit:	-30°C
Hitzeresistenz:	+70°C